



Technical Data Sheet: CreatBot PETG-ESD

Print parameters	
Project	Data
Pre-printing drying conditions	50-60℃ , 6-8 H
Nozzle temperature	240-260℃
Nozzle Diameter	0.4 / 0.6 / 0.8 / 1.0 mm
Print bed surface treatment	3D Printing Spray / PVP Glue Stick / Specialized Adhesive
Print bed temperature	70-90℃
Chamber temperature	/
Cooling fan speed	40-90%
Print speed	< 300 mm/s

Physical Properties	Test method	Data
Density	ISO1183	1.22g/cm³
Saturated water absorption rate	25℃ , 55%RH	/
Melt index	230℃ , 5 kg	18.1g/10 min
Melting temperature	DSC, 10℃/ min	/
Vicat softening temperature	ISO 306,GB/T 1633	/
Determination of temperature	ISO 75 , 0.45MPa	68℃

Mechanical Properties	Test method	Data
Tensile strength XY	ISO 527, GB/T 1040	48 MPa
Tensile strength Z	ISO 527, GB/T 1040	19 MPa
Young's modulus XY	ISO 527, GB/T 1040	/
Young's modulus Z	ISO 527, GB/T 1040	/
Elongation at break XY	ISO 527, GB/T 1040	8.6%
Elongation at break Z	ISO 527, GB/T 1040	2.4%
Bending strength XY	ISO 178, GB/T 9341	76 MPa
Bending strength Z	ISO 178, GB/T 9341	41 MPa
Bending modulus XY	ISO 178, GB/T 9341	2150 MPa
Bending modulus Z	ISO 178, GB/T 9341	1450 MPa
Notched Impact strength XY	ISO 179, GB/T 1043	4.95 kJ/m²
Notched Impact strength Z	ISO 179, GB/T 1043	1.93 kJ/m²

Disclaimer:

The above material performance data is from the CreatBot Laboratory and is intended solely for reference and comparison.

Actual 3D-printed model performance varies based on multiple factors, such as the printer, printing conditions, model geometry, and slicing software settings.

Users assume full responsibility for the legality and safety of their 3D printing when using CreatBot materials.

CreatBot is not liable for the application or use of its filaments, nor for any damages incurred during the use of our products.